

C. L. Hauthaway & Sons Corporation
638 Summer Street Lynn, MA 01905-2092

781 592-6444
www.hauthaway.com

Hauthane L-3786

- DESCRIPTION:** A self-crosslinking, aliphatic, water-based polyurethane dispersion designed for use in high performance concrete and wood floor coatings.
- SUGGESTED USES:** **L-3786** employs a unique air-dry, self-crosslinking mechanism to impart chemical-resistance, abrasion-resistance and mar-resistance properties which equal or exceed those of two-component, water-based floor coating systems currently used in the market.
- CHARACTERISTICS:**
- < One-component, self-crosslinking polymer
 - < High level of toughness, abrasion- and mar-resistance
 - < Outstanding water and chemical resistance
 - < Excellent exterior weathering performance
 - < Contains dipropylene glycol dimethylether (DMM) co-solvent
- APPLICATION:** **L-3786** can be used as a sole vehicle or blended with acrylic emulsions for spray, brush or roller applications. Rheology modifications can be made with associative thickeners to optimize application properties.
- DRYING:** Ambient drying temperatures between 60 – 90° F are ideal to produce coatings with optimal film properties. Coatings based on **L-3786** require 3 – 5 days to achieve full performance properties, but floor applications are accessible by light foot traffic within 24 hours.

PHYSICAL PROPERTIES*

SOLIDS	32% (± 1%)
VISCOSITY	50-300 cps
pH	7.0-10.0
DENSITY	8.8 lbs/gal
SOFTENING POINT	NA ° F
VOC CONTENT	236 g/l (less water)
VOC CONTENT	99 g/l (as supplied)

TENSILE PROPERTIES**

(TESTED AT 20 INCHES/MINUTE)	
ELONGATION	160 %
TENSILE STRENGTH	2400 psi
100% MODULUS	1850 psi
200% MODULUS	NA
300% MODULUS	NA

*Provisional – Physical properties are considered provisional until at least 10 production batches have been produced.

**Films are coalesced with 3% DPM to ensure optimal film formation.